

Nitoproof 650PU

Polyurethane based Liquid applied two component elastomeric water proofing membrane.

Uses

Nitoproof 650 PU is used to provide a continuous, seamless, water and vapour proof membrane for concrete. Typical applications will include roofs, podiums, balconies, floor slabs, suspended floors, inspection pits, after bridge decks basement retaining wall.

Advantages

- Solvent free non-toxic formulation
- Pitch free Polyurethane
- Cures to form a permanently flexible, resilient barrier over a wide range of temperatures
- Root Resistance*
- Excellent continuous adhesion to concrete prevents lateral water migration
- Irreversible chemical cure does not permit melting or flow of film at elevated ambient temperatures
- Capable of bridging substrate cracks up to 3.7mm
- Easy to apply, requires no special equipment

* Protection screed required

Description

Nitoproof 650 PU is a two component liquid polyurethane. It cures to form a tough, elastomeric, waterproof membrane Nitoproof 650PU is designed for use on horizontal and vertical surfaces, covered by a protective screed/protection board.

Technical support

Fosroc offers comprehensive technical support, including help at the design stage, application advice and on site problem solving. Specifiers and contractors are encouraged to contact our trained staff for answers to their questions.

For further information please contact Fosroc

Typical Properties

Service temperature range	: - 35°C to +80°C
Tack free time @ 25°C	: < 5 hours
Mixed gravity	: 1.5 +/- 0.1
Solids content(%)	: 98

Typical results from membrane cured for 28 days:

Elongation (%) (ASTM D412)	: > 600%
Tensile Strength (N/mm ²) (ASTM D412)	: > 6
Adhesion to concrete ASTM D903) (ASTM D903)	: > 2N/mm ²
Tear Resistance	: 30 N/mm
Moisture Vapour transmission (g/sq.m/hr) (ASTM E96)	: 0.4
Initial hardness (Shore A) (ASTM 2240)	: 67
Puncture Resistance (ASTM E 154)	: > 170 N
Resistance to water pressure DIN EN 1928	: No leak
Thermal Resistance	: Pass@80°C for 100 days
Fire Resistance	: Class F
Resistance to plant root EN 13948	: Pass
Crack Bridging (ASTM C836)	: 3.7mm
Chemical resistance	: Unaffected by mild acids, alkalis and water borne salts. Does not biodegrade.

Specification clauses

Supplier Specification

Where shown on the drawings, the liquid applied, elastomeric polyurethane waterproof membrane shall be Nitoproof 650PU obtained from Fosroc. It shall be used in accordance with the manufacturer's current application instructions.

Performance Specification

The liquid applied, elastomeric waterproofing membrane, where shown on the drawings, shall be made of hydrocarbon free polyurethane. The membrane when cured shall be capable of an extension of not less than 600%. Its tensile strength shall exceed 6N/mm and the moisture vapour transmissions shall be less than 0.4 g/mm²/24 hour. It shall be used in accordance with the methods given in the manufacturer's data sheet.

Nitoproof 650PU

Application instructions

Preparation

All surfaces to be waterproofed should be clean, sound and dry. Priming for good quality, dense concrete is not necessary. For absorbent surfaces such as porous concrete a mixture of 1 part Nitoproof 650PU and 1 part of Nitofl or Sol is used to seal the surface.

Mixing

The two components Part A and Part B should be mixed in the ratio of 1:1 with a slow speed drill at 500 rpm for 3-4 min. The mix should be immediately used within 30 minutes

Cracks

Shrinkage and non-moving cracks should be pre-treated with not less than 1.5 mm thick coating of Nitoproof 650PU extending minimum 50mm either side of the crack. A layer of reinforcement cloth can be sandwiched in between the 2 coats, Allow to cure before general application.

Right Angle Bends

All right angle bends must have a minimum 25 x 25mm angle fillet installed prior to application of Nitoproof 650PU. All angle joints, protrusions and stress points should be pretreated with an additional application of Nitoproof 650PU extending 50 -100mm either side of the detail. Any pretreated areas must be cured overnight before general application of the membrane.

Application Methods

Nitoproof 650PU can be applied by brush, squeegee or roller. If applied in 2 coats, the second coat should be applied in perpendicular direction to the first coat. Where required, Nitoproof 650PU may be reinforced using a suitable fabric reinforcement. For consumption, more than 1.5 kg, can be applied in 2 coats. For consumption less than 1.5 kg per Sqm, can be applied in a single coat. Please contact your local Fosroc office for details.

The newly applied membrane must be allowed to cure for a minimum 24 hours at 25°C. Tools and equipment should be clean with suitable solvent immediately after use.

Flood Test

Prior to placement of protection, flood to a minimum depth of 50mm of water for 24 hours. Drains shall be plugged and barriers placed to contain the water.

Cleaning

Tools and equipment should be cleaned with a suitable solvent immediately after use. Do not use the solvent for thinning.

Limitations

Nitoproof 650PU should be protected from UV light not more than 14 days after application. This can normally be achieved by use of a protective screed/board.

Estimating

Supply

Nitoproof 650PU (Mixing ratio 1:1)	: 20 kg pail Part A 20kg pail Part B
---------------------------------------	---

Coverage	: 1.5kg/sqmt corresponds to dry film thickness of 1.07mm
----------	---

Storage

Shelf life

Minimum 9 months in original unopened containers if kept below 25°C.

Note : In accordance with Commercial or Health & Safety requirements packaging detail may alter. Please contact your local Fosroc office for detail.

Precautions

Health and safety

Some people are sensitive to resin systems. Impervious gloves and barrier cream should be used when handling these products. Eye protection should be worn. If accidental eye contamination occurs, wash thoroughly with plenty of water and seek medical advice. If contact with skin occurs, it must be removed before curing takes place. Wash off with an industrial skin cleaner followed by plenty of soap and water. Do not use solvent. Ensure adequate ventilation when using these products.

Fire

Nitoproof 650PU is flammable. Keep away from sources of ignition. No smoking. In the event of fire, extinguish with CO² or foam. Do not use a water jet.

Flash point:	56°C
--------------	------

For further information, refer to the Product Material Safety Datasheet.



Nitoproof 650PU



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point
No.150, 2nd Floor,
Infantry Road,
Bangalore-560001

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-42521900

fax

++91 80-22281510

e-mail

enquiryindia@fosroc.com

Regional Offices

Chennai

Hills Center, Old No.5, New No.9
3rd Cross Street, Jeth Nagar,
Raja Annamalaipuram,
Chennai 600 028
Ph: +91 44 24899949-94
Fax: 044-24896641

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800
Fax: 022 62296809

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph:+91 33-65343188
Fax: 033-2499-0280